



Contribution ID: 91

Type: Student Poster

Post-Compression of High-Power CO₂ Lasers to sub-ps Levels Using an Ultrathin Tailored Nonlinear Element for Advanced Accelerator Applications

Tuesday, November 8, 2022 5:00 PM (2h 30m)

High-power long-wavelength infrared lasers (e.g. CO₂ laser) are of great interest for acceleration of electrons and ions. For LWFA, pulses as short as 300-500fs are required to drive relativistic plasma wakes at 10^{16} - 10^{17} cm⁻³ densities. The shortest pulse length demonstrated so far in CO₂ lasers is 2ps; these multiterawatt pulses are generated using a multistage MOPA system at ATF BNL.

One way to generate sub-picosecond pulses is post-compression of longer pulses after final amplification. Current LWIR post-compression schemes involve two stages of bulk materials; the first stage provides spectral broadening via self-phase modulation, while the second stage with negative GVD compresses the pulse. This arrangement has been experimentally demonstrated [1,2]. A main drawback is inhomogeneity of compression along the beam's radial distribution, leading to inefficient use of energy and unwanted spatio-temporal coupling.

At UCLA, we have been studying nonlinear optical responses of LWIR transparent semiconductor materials over the last several years using picosecond CO₂ laser pulses and, recently, with a newly acquired sub-picosecond solid-state-based OPA/DFG system. We measure nonlinearities of GaAs, n-Ge, and ZnSe for <1ps long, 10μm pulses and show they are close to literature data, however the Kerr nonlinearity of Te, never reported before, is extremely high on the order of $\geq 5 \times 10^{-12}$ cm²/W. We propose and numerically show how an ultrathin and radially engineered Te nonlinear optical chirping element can be used for generation of homogeneous spectral broadening of an initially picosecond CO₂ laser pulse.

Modeling of post-compression is done by solving the 2D nonlinear Schrödinger equation. Using 2ps Gaussian pulses containing 400mJ centered at 9.2μm, similar to that in [2], sufficient broadening is achieved in a Te layer ~50μm thick. A structured layer with Gaussian thickness is used to give identical spectral broadening across the full beam. The pulse is then numerically propagated through 5 cm of BaF₂, after which it is compressed to a pulse duration less than 300 fs, homogenous across the whole beam. This compression results in a several times increase in peak-power. One can foresee that thin film and etching technology could be used for fabrication of such a large aperture pulse compressor.

Acknowledgments

Work supported by ONR MURI N00014-17-1-2705.

Primary authors: MATTEO, Daniel (UCLA Department of Electrical Engineering); TOCHITSKY, Sergei (UCLA Department of Electrical Engineering); JOSHI, Chan (UCLA Department of Electrical Engineering)

Presenter: MATTEO, Daniel (UCLA Department of Electrical Engineering)

Session Classification: Poster Session and Reception

Track Classification: Poster Session: WG8 Poster: Advanced Laser and Beam Technology and Facilities